

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 April 2004 (29.04.2004)


PCT

(10) International Publication Number
WO 2004/035873 A1

- (51) International Patent Classification⁷: **C25C 5/00**,
C22B 9/14, 34/12
- (21) International Application Number:
PCT/AU2003/001364
- (22) International Filing Date: 15 October 2003 (15.10.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2002952083 16 October 2002 (16.10.2002) AU
- (71) Applicant (for all designated States except US): **BHP BILLITON INNOVATION PTY LTD** [AU/AU]; BHP Billiton Centre, 180 Lonsdale Street, Melbourne, Victoria 3000 (AU).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **STREZOV, Les** [AU/AU]; 7 Marin Street, Adamstown, New South Wales 2289 (AU). **RATCHEV, Ivan** [AU/AU]; 2 Young Street, Georgetown, New South Wales 2298 (AU). **OSBORN, Steve** [AU/AU]; 15 Robertson Road, Valentine, New South Wales 2280 (AU). **BLIZNYUKOV, Sergey, Alexander** [RU/AU]; 13/52 Robert Street, Jesmond, New South Wales 2299 (AU).
- (74) Agent: **GRIFFITH HACK**; 509 St Kilda Road, Melbourne, Victoria 3004 (AU).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),

[Continued on next page]

(54) Title: MINIMISING CARBON TRANSFER IN AN ELECTROLYTIC CELL



(57) **Abstract:** An electrochemical cell for electrochemical reduction of a metal oxide in a solid state is disclosed. The cell includes a molten electrolyte (14), an anode (18) formed from carbon in contact with the electrolyte, a cathode (20) formed at least in part from the metal oxide in contact with the electrolyte, and a membrane (28) that is permeable to oxygen anions and is impermeable to carbon in ionic and non-ionic forms positioned between the cathode and the anode to thereby prevent migration of carbon from the anode to the cathode. The membrane includes a body (32) and a lining (34) on the surface of the body on the cathode side of the membrane. The lining is formed from a material that is inert with respect to dissolved metal in the electrolyte and is impermeable to the dissolved metal. An electrochemical method based on the cell is also disclosed.



Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*